



Dehui Industry Company Limited  
 Tel:+865466392306 Fax:+865466392307 www.dhfilmtech.com  
 Email:info@dhfilmtech.com

### Test Report

<b>Product Name</b>		PET Heat Sealable Films	<b>Grade</b>	A
<b>Type</b>		RFC110	<b>Thickness</b>	23um
<b>Surface treatment</b>		in	<b>Tester</b>	张丽琴
<b>Item</b>		<b>Unit</b>	<b>Test Method</b>	<b>Value</b>
<b>Thickness</b>		μm	ASTM D374	23.4
<b>Tensile strength</b>	<b>MD</b>	MPa	ASTM D882	251
	<b>TD</b>			243
<b>Elongation</b>	<b>MD</b>	%		93
	<b>TD</b>			84
<b>Heat Shrinkage</b>	<b>MD</b>	%	150°C/30min	0.5
	<b>TD</b>			0
<b>Haze</b>		%	ASTM D1003	2.4
<b>Transmittance</b>		%		91
<b>Gloss</b>		%	GB/T 8807 (45°)	114
<b>C.O.F(IN/OUT)</b>		μs/μk	ASTM D1894E	0.37/0.35
<b>Wet Tension</b>		mN/m	ASTM D2578	60
<b>Heat Sealing Strength</b>		N/15mm	120°C/80°C /135Kpa/2S	3.71